



ESL ELECTROSCIENCE

CERAMIC TAPES &
THICK-FILM MATERIALS

416 EAST CHURCH ROAD
KING OF PRUSSIA, PA 19406-2625, U.S.A

T: 610-272-8000
F: 610-272-6759

www.electroscience.com

PARTIALLY STABILIZED ZIRCONIA TAPE

42013-A

RoHS compliant* high temperature PSZ tape for use in planar sensors

ESL 42013-A is a flexible cast film of partially stabilized zirconia (PSZ) powder dispersed in an organic matrix. This material is designed to be sintered in the temperature range of 1450°C-1550°C to yield a dense white-colored ceramic. ESL 42013-A tape is provided on a silicone-coated polyester film to protect the tape from mechanical damage and aid in handling.

This tape is generally used with Pt inks (ESL 5570 Series) that can be co-fired for use in planar sensors.

TYPICAL PROPERTIES:

TAPE THICKNESS: 125 $\mu\text{m} \pm 10\%$
(custom thicknesses available)

PROCESSING:

Parts are formed by blanking sheets of the tape to the required green size prior to sintering. The burnout cycle depends on the part configuration and size.

TYPICAL PEAK SINTERING TEMPERATURE FOR PARTS: 1500°C for 3 hours

STABILIZING AGENT: Y_2O_3

STABILIZER CONTENT: 5.0 mol %

FIRED SHRINKAGE: X: 17.3 ± 1.0 %
(12-layer bar fired at 1500°C for 3 hours) Y: 18.3 ± 1.0 %

FIRED DENSITY: $\geq 97\%$ of theoretical
(1500°C for 3 hours)

ESL Europe (KOP) 42013-A 1004-New

ESL Affiliates

ESL Europe (Agmet Ltd) • 8 Commercial Road • Reading • Berkshire • England • RG2 0QZ • Tel: +44 (0) 118 918 2400 • Fax: +44 (0) 118 986 7331 • Sales@ESLEurope.co.uk

ESL Nippon • Sukegawa Bldg. • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: +81-3-3864-8521 • Fax: +81-3-3864-9270 • Sales@ESL-Nippon.co.jp

ESL China • Room #1707, Tower A, City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051 • Tel: +86-21-6237-0336 and 0337 • Fax: +86-21-6237-0338
ESLChina@eslshanghai.net

See Caution and Disclaimer on other side.

Blank page

ESL Europe (KOP) 42013-A 1004-New

*None of the six substances referred to in the RoHS Directive (2002/95/EC) are used in the formulation of this product.

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapours emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. ElectroScience assumes no liability for any injury, loss, or damage, direct or consequential, arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular use, before using it. User assumes all risk and liability whatsoever in connection with his intended use. ElectroScience's only obligation shall be to replace such quantity of the product proved defective.
