



## ESL ELECTROSCIENCE

CERAMIC TAPES &  
THICK-FILM MATERIALS

416 EAST CHURCH ROAD  
KING OF PRUSSIA, PA 19406-2625, U.S.A

T: 610-272-8000  
F: 610-272-6759

[www.electroscience.com](http://www.electroscience.com)

# POLYMER SILVER CONDUCTOR

# 1107-S

**RoHS Compliant\***

ESL 1107-S is a phenolic based, silver filled, thermosetting conductive polymer that exhibits a very smooth surface. It can be nickel plated by electroless techniques to enhance solder leach resistance and solderability.

## PASTE DATA

**Rheology:** Thixotropic, screen-printable paste

**Viscosity:**  
(Brookfield RVT, 10 rpm  
ABZ Spindle, 25.5 ± 0.5 °C) 80 ± 20 Pa.s

**Shelf Life:** 6 months  
(Material will dry when in contact with air. Refrigerated storage is recommended)

## PROCESSING

**Screen Mesh, Emulsion:** 200-325 S/S, 25 µm

**Levelling Time (20°C):** 5 - 10 min

**Drying Time (at 125°C):** 10 - 15 min

**Curing Schedules:**  
Ventilated Box Oven: 150°C / 2hrs  
IR Furnace: 220°C peak / 3 - 4 min

**Substrate for Calibration:** 96% alumina

**Thinner:** ESL 402

ESL Europe (KOP) 1107-S 9807-G

### ESL Affiliates

ESL Europe (Agmet Ltd) • 8 Commercial Road • Reading • Berkshire • England • RG2 0QZ • Tel: +44 (0) 118 918 2400 • Fax: +44 (0) 118 986 7331 • Sales@ESLEurope.co.uk

ESL Nippon • Sukegawa Bldg. • 6<sup>th</sup> floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: +81-3-3864-8521 • Fax: +81-3-3864-9270 • Sales@ESL-Nippon.co.jp

ESL China • Room #1707, Tower A, City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051 • Tel: +86-21-6237-0336 and 0337 • Fax: +86-21-6237-0338  
ESLChina@eslshanghai.net

See Caution and Disclaimer on other side.

## TYPICAL PROPERTIES

<b>Cured Thickness:</b>	25 ± 7 µm
<b>Approximate Coverage:</b>	150 cm <sup>2</sup> / g
<b>Resistivity:</b>	<40 mΩ/sq.
<b>Printing Resolution:</b> (line/space)	0.250 mm / 0.250 mm
<b>Solder Wettability:</b> (RMA Flux, 2 sec. dip, 62Sn/36Pb/2Ag, 220°C)	Very good to excellent
<b>Compatibility:</b>	240-SB Polymer

ESL Europe (KOP) 1107-S 9807-G

---

\*None of the six substances referred to in the RoHS Directive (2002/95/EC) are used in the formulation of this product.

**CAUTION:** Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapours emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

**DISCLAIMER:** The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. ElectroScience assumes no liability for any injury, loss, or damage, direct or consequential, arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular use, before using it. User assumes all risk and liability whatsoever in connection with his intended use. ElectroScience's only obligation shall be to replace such quantity of the product proved defective.

---